



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



Publication number: **0 505 162 A1**

(12)

# EUROPEAN PATENT APPLICATION

(21) Application number: **92302327.9**

(22) Date of filing: **18.03.92**

(51) Int. Cl.<sup>5</sup>: **C08G 69/26, C08L 77/02, C08L 23/08, C08K 7/02, C08K 9/06, C08L 51/06, // (C08K7/02, C08L77:02, 23:08), (C08K7/02, C08L77:02, 51:06)**

(30) Priority: **18.03.91 JP 52875/91**

(43) Date of publication of application:  
**23.09.92 Bulletin 92/39**

(64) Designated Contracting States:  
**FR GB IT**

(71) Applicant: **TORAY INDUSTRIES, INC.**  
**2-1, Nihonbashi Muromachi 2-chome Chuo-ku**  
**Tokyo (JP)**

(72) Inventor: **Onishi, Koji**  
**470-18, Tozu, Tado-cho**  
**Kuwana-gun, Mie (JP)**  
Inventor: **Kataoka, Shiro**  
**Toray Atsuta-ryo, 4-1, Sanjo 2-chome**  
**Minami-ku, Nagoya-shi, Aichi (JP)**  
Inventor: **Iwamoto, Masatoshi**  
**51-1, Uguiura Higashikidoke, Yatomi-cho**  
**Ama-gun, Aichi (JP)**

(74) Representative: **Coleiro, Raymond et al**  
**MEWBURN ELLIS 2 Cursitor Street**  
**London EC4A 1BQ (GB)**

(54) **Polyamide blow molded product.**

(57) A resin composition contains a copolyamide having a melting point of 225°C or more and a crystallization temperature of 230°C or less and obtained by polymerization of 66, 6T and 6I components at a specific compounding ratio. Parisons which are both long and of a three-dimensionally curved shape can be moulded from the composition in a stable manner.

EP 0 505 162 A1

## BACKGROUND OF THE INVENTION

## 1. Field of the Invention

The present invention relates to a polyamide blow molded product having superior mechanical properties, chemical resistance and heat resistance, and more specifically, to a three-dimensionally curved polyamide blow molded product wherein the hollow molded product has a non-linear shape.

## 2. Description of the Related Art

As polyamides generally demonstrate little change in melt viscosity with respect to shear rate, various attempts have been made to obtain a blow molded product (see: Japanese Examined Patent Publication (Kokoku) No. 48-7509, Japanese Unexamined Patent Publication (Kokai) Nos. 50-2790, 50-2791, 50-3193, 50-104297, 52-32044, and 53-21252 and Japanese Examined Patent Publication (Kokoku) No. 55-41659).

Automotive parts are now required to have an increasingly lighter weight, for a conservation of energy, and accordingly, plastics are now commonly used as an alternative to metal. Moreover, since parts such as those located in the engine compartment are subjected to high temperatures (80 - 130°C), such parts are also required to have a good heat resistance.

Although Nylon 66 is generally used as a polyamide having a favorable heat resistance and able to be blow molded, due to the favorable crystallization and rapid crystallization rate of Nylon 66, solidification begins on the end of the parison when the parison is extracted, thus allowing only hollow molded products having incomplete shapes to be obtained.

As in the case of three-component copolyamides comprising hexamethylene terephthalamide (6T), hexamethylene isophthalamide (6I) and hexamethylene adipamide (66), it is known that polyamides in which aromatic units are introduced into the molecular chain have an improved heat resistance and chemical resistance (Japanese Unexamined Patent Publication (Kokai) Nos. 52-78298, 55-62958, 59-155426, 61-200123, 61-94842, 63-120645, 1-176555, and 3-7761 and Japanese Examined Patent Publication (Kokoku) Nos. 44-22214, 45-21116, 46-28218, 55-31206, and 55-41335, and Japanese Unexamined Patent Publication (Kokai) Nos. 52-132150, 61-618, 61-63785 and 63-308065).

Although increasing the composite ratio of the 6T component generally improves the heat resistance, due to the high crystallization temperature and rapid crystallization rate, a rapid solidification of the parison occurs, and accordingly, the blow moldability is not improved in comparison to Nylon 66. Further, when the composite ratio of the 6I component is increased, due to the low crystallization temperature and slow crystallization rate, a slow solidification of the parison occurs. Although this results in an improvement of the blow moldability, the heat resistance becomes poor due to a lowering of the melting temperature.

## SUMMARY OF THE INVENTION

The present invention seeks to minimize or eliminate the abovementioned disadvantages of the prior art and to this end provides a polyamide blow molded product obtained from a three-component polyamide comprising 6T, 6I and 66 and having a slow crystallization rate and a large dependency of the melt viscosity on the shear rate, without impairing the heat resistance.

In accordance with the present invention, there is provided a polyamide blow molded product comprising: a crystalline polyamide comprising (a) 50 - 90% by weight of a hexamethylene azipamide component, (b) 5 - 40% by weight of a hexamethylene terephthalamide component, and (c) 5 - 30% by weight of a hexamethylene isophthalamide component, wherein the melting point (Tm) and crystallization temperature (Tc) of the crystalline polyamide are  $T_m \geq 225^\circ\text{C}$  and  $T_c \leq 230^\circ\text{C}$ , respectively.

In accordance with the present invention, there is also provided a polyamide blow molded product comprising: a crystalline polyamide comprising (a) 53 - 85% by weight of a hexamethylene azipamide component, (b) 15 - 40% by weight of a hexamethylene terephthalamide component, and (c) 5 - 20% by weight of a hexamethylene isophthalamide component; wherein the melting point (Tm) and crystallization temperature (Tc) of the crystalline polyamide are  $T_m \geq 240^\circ\text{C}$  and  $T_c \leq 230^\circ\text{C}$ , respectively.

## DESCRIPTION OF THE PREFERRED EMBODIMENTS

The inventors of the present invention conducted intensive studies into ways in which to obtain a polyamide having a slow crystallization rate, and a large dependency of the melt viscosity on the shear rate, as a material for blow molding, by lowering the crystallization rate without impairing the heat resistance for a three-component

copolyamide comprising the components of 6T, 6I and 66.

As a result of the studies conducted to solve the above-mentioned problems, the inventors arrived at the present invention by discovering that copolyamides having a composition within a specific composition range are able to solve all of the above-mentioned problems.

5 Namely, the preferred embodiment of the present invention provides:

(1) a polyamide blow molded product comprising: a crystalline polyamide comprising (a) 50 - 90% by weight of a hexamethylene adipamide component, (b) 5 - 40% by weight of a hexamethylene terephthalamide component, and (c) 5 - 30% by weight of a hexamethylene isophthalamide component; wherein the melting point (T<sub>m</sub>) and crystallization temperature (T<sub>c</sub>) are T<sub>m</sub> ≧ 225°C and T<sub>c</sub> ≧ 230°C, respectively; and wherein, when measured at a constant temperature of 20°C higher than the melting point (T<sub>m</sub>) of said polyamide  
10 (T<sub>m</sub> + 20°C), the melt viscosity of said polyamide is such that:

$$2,000,000 \geq \ln \mu_{a10} \geq 2,000 \quad (I)$$

and,

$$\mu_{a10}/\mu_{a1000} \geq 3.3 \quad (II)$$

15 wherein:

T<sub>m</sub>: melting point of polyamide (°C)

μ<sub>a10</sub>: melt viscosity at a temperature of T<sub>m</sub> + 20°C and a shear rate of 10 (1/sec) (poise)

μ<sub>a1000</sub>: melt viscosity at a temperature of T<sub>m</sub> + 20°C and a shear rate of 1000 (1/sec) (poise); and moreover,

20 (2) a polyamide blow molded product comprising various polyamide compounds wherein a polyamide having the above-mentioned characteristics is mutually combined with a fibrous reinforcing material, elastomer, flame retarder, and so on; and wherein, when measured at a constant temperature of 20°C higher than the melting point (T<sub>m</sub>) of said polyamide (T<sub>m</sub> + 20°C), the melt viscosity of said polyamide compound is such that:

$$2,000,000 \geq \ln \mu_{a10} \geq 2,000 \quad (I)$$

and,

$$\mu_{a10}/\mu_{a1000} \geq 3.3 \quad (II)$$

wherein:

T<sub>m</sub>: melting point of polyamide (°C)

30 μ<sub>a10</sub>: melt viscosity at a temperature of T<sub>m</sub> + 20°C and a shear rate of 10 (1/sec) (poise)

μ<sub>a1000</sub>: melt viscosity at a temperature of T<sub>m</sub> + 20°C and a shear rate of 1000 (1/sec) (poise); and,

(3) a polyamide blow molded product wherein a blow molded product has a three-dimensionally curved shape.

The polyamide usable in the present invention is a polyamide in which the components are adjusted within  
35 a component range of (a) 50 - 90% by weight of a component 66, (b) 5 - 40% by weight of component 6T and (c) 5 - 30% by weight of component 6I, and more preferably, (a) 53 - 85% by weight of component 66, (b) 15 - 40% by weight of component 6T and (c) 5 - 20% by weight of component 6I. When the amount of component 66 is less than 50% by weight, the resulting polyamide has a low degree of crystallinity and the balance between the properties thereof, such as a chemical resistance, is poor. When the amount of component 66 is more than  
40 90% by weight, the crystallization temperature is more than 230°C, and thus a parison having a required length cannot be obtained during blow molding. Further, when the amount of component 6T is less than 5% by weight, the melting point of the resulting polyamide is lower than 255°C resulting in a lower heat resistance and a poor balance between the properties thereof. When the amount of component 6T is more than 40% by weight, although the heat resistance is improved the crystallization temperature exceeds 230°C, and this promotes a solidification of the parison during blow molding. Moreover, when the amount of component 6I is less than 5%  
45 by weight, the resulting polyamide essentially becomes a 66/6T copolymer, and although the heat resistance is improved the crystallization temperature is more than 230°C, and this promotes a solidification of the parison during blow molding. When the amount of component 6I is more than 30% by weight, the melting point of the resulting polyamide is lowered due to the non-crystalline nature of the 6I component, which results in a loss of  
50 both the crystallinity and heat resistance thereof. Namely, the polyamide of the present invention is based on the design concept of lowering the crystallization temperature of Nylon 66 by introducing a component 6I, and compensating for the lowering in the heat resistance due to the introduction of component 6I, while also improving the blow moldability by the addition of a component 6T. When a design concept other than this is used, a polyamide that allows blow molding while maintaining a balance between properties cannot be obtained.

Moreover, to obtain a polyamide satisfying the conditions of T<sub>m</sub> ≧ 225°C, more preferably T<sub>m</sub> ≧ 240°C, and further, T<sub>c</sub> ≧ 230°C, detailed polymerization tests were conducted within the above-mentioned component ranges for the 66, 6T and 6I components, and thereafter, the T<sub>m</sub>, T<sub>c</sub>, and crystallinity of the resulting polyamides were measured with a differential scanning calorimeter (DSC), to determine the amounts of each component.

The polymerization methods used for the polyamide included melt polymerization, interfacial polymerization, solution polymerization, block polymerization, solid phase polymerization, and combinations thereof. Melt polymerization is generally most preferable. The raw materials of each of the components may be loaded into a polymerization oven in the form of 66, 6T and 6I salts, or in the form of respective monomers thereof.

Although there is no particular limit to the degree of polymerization of the polyamide used, a polyamide in which the relative viscosity, measured by dissolving 1g of polymer in 100 ml of 98% concentrated sulfuric acid at 25°C, is to be treated similarly hereinafter, is within 1.5 or more to less than 5 is preferable, based on the stable discharge from the polymerization oven. Further, the addition of monocarboxylic acid compounds, dicarboxylic acid compounds, monoamine compounds, diamine compounds and their derivatives as polymerization stabilizers to the polymerization oven, together with the monomers, followed by polymerization is an effective method of obtaining a stable discharge of the polymer from the polymerization oven. Examples of these compounds include acetic acid, benzoic acid, stearic acid, sebacic acid, adipic acid, didodecanic acid, undecanic acid, terephthalic acid, isophthalic acid, suberic acid, cyclohexane dicarboxylic acid, stearylamine, ethylenediamine, decamethylenediamine, tetramethylenediamine, and hexamethylenediamine.

Also, interrupting the polymerization at a low degree of polymerization can be used as a method of facilitating the stability when discharging the polymer from the polymerization oven. A low degree of polymerization refers to a relative viscosity ( $\eta_r$ ) of 1.02 - 1.6. A solid phase polymerization or melt polymerization in a melt extruder is an effective means of converting polymers having a low degree of polymerization into polymers having a high degree of polymerization, with a relative viscosity ( $\eta_r$ ) of 1.5 - 6.0.

The melting temperature of the polyamide used is 225°C or higher, preferably 240°C or higher. When the melting point is lower than 225°C, a desired heat resistance cannot be obtained. Although the upper limit of the melting point is not particularly specified, a temperature of 300°C or less is preferable from the viewpoint of an easy manipulation thereof during polymerization and an easy molding. A crystallization temperature of 230°C or lower effectively obtains a long parison. When this temperature is higher than 230°C, a solidification of the parison rapidly occurs, thus preventing the obtaining of a parison having a considerable length. Although there is no particular limit to the lower limit of the crystallization temperature, a temperature which allows crystallization at room temperature, i.e., a temperature of around 40°C, is generally considered preferable. Although there are no particular restrictions on the crystallinity, a semi-crystallization time also can be used in addition to a crystallization temperature, as a measure of the crystallization rate serving as a reference for obtaining a long parison. Where the polyamide is within the component ranges of the present invention, the semi-crystallization time as measured by DSC at a melting point of -20°C is 400 seconds or more, and such a polyamide having a semi-crystallization time equal to or greater than this value can be used without difficulty.

In general, polyamides demonstrate small changes in melt viscosity with respect to the shear rate, i.e., have melt viscosity characteristics depending little on the shear rate. Consequently, when blow molding using a conventional screw type blow molding machine, although the raw material polymer is plasticized by the large shear rate in the screw, preferably the melt viscosity is low from the viewpoint of the motive power of the extruding machine, and of productivity. When forming a parison from a melted polymer, however, preferably the polymer has a high melt viscosity at low shear rates, to thus adequately maintain the shape of the polymer melt extruded from the nozzle and obtain a uniform dimension and wall thickness of the molded product. Thus, although most preferably the melt viscosity is high, to obtain large blow molded products having a favorable dimensional stability, this condition will not be satisfied if only the melt viscosity of the raw material polymer is high; the raw material polymer must satisfy the extremely important condition of a melt viscosity greatly dependent upon the shear rate.

The blow moldability of the polyamide raw material was determined by measuring the melt viscosity (poise)  $\mu\text{a}10$  and  $\mu\text{a}1000$  at shear rates of 10 ( $\text{sec}^{-1}$ ) and 1000 ( $\text{sec}^{-1}$ ) and at a melting point of  $T_m + 20^\circ\text{C}$ , using a melt indexer manufactured in compliance with ASTM-D-1238. Preferably, the dependency of the melt viscosity on the shear rate is within the range stipulated in equations (I) and (II) below.

$$2,000,000 \geq \ln \mu\text{a}10 \geq 2,000 \quad (\text{I})$$

$$\mu\text{a}10/\mu\text{a}1000 \geq 3.3 \quad (\text{II})$$

wherein:

$T_m$ : melting point of polyamide ( $^\circ\text{C}$ )

$\mu\text{a}10$ : melt viscosity at a temperature of ( $T_m + 20^\circ\text{C}$ ) and a shear rate of 10 (1/sec) (poise)

$\mu\text{a}1000$ : melt viscosity at a temperature of ( $T_m + 20^\circ\text{C}$ ) and a shear rate of 1000 (1/sec) (poise); and preferably:

$$1,500,000 \geq \ln \mu\text{a}10 \geq 3,000 \quad (\text{I})$$

$$\mu\text{a}10/\mu\text{a}1000 \geq 4.0 \quad (\text{II})$$

The copolyamide alone, as well as various types of polyamide compounds prepared from the copolyamide and additives such as a fibrous reinforcing material, elastomer, flame retarder, heat resisting agent, antioxidant

or flame retarder assistant, may be applied to equations (I) and (II).

The addition of the fibrous reinforcing material used in the present invention is able to provide a rigidity and a high thermal deformation temperature in the raw arterial polyamide compound. These fibrous reinforcing materials may be untreated or surface treated with a silane-based coupling agent such as triethoxy- $\gamma$ -aminopropylsilane, N- $\beta$ -(aminomethyl)- $\gamma$ -aminopropyltrimethoxysilane, vinyltriethoxysilane or  $\gamma$ -glycidoxypropyltrimethoxysilane having a favorable thermal stability. Also, two or more types of these fibrous reinforcing materials may be used. Moreover, in addition to a fibrous reinforcing material, inorganic fillers such as talc, kaolin, gypsum, mica, quartz, calcium carbonate, magnesium hydroxide, calcium phosphate, titanium phosphate, sericite, anhydrous mica, wollastonite, diatomaceous earth, clay, white carbon, carbon black and zinc powder, may be added.

Preferably 1 - 200 parts by weight are blended, more preferably 10 - 100 parts by weight, of the fibrous reinforcing material of the present invention into 100 parts by weight of polyamide. When the blended amount of reinforcing material is 200 parts by weight or more, the characteristics of the polyamide cannot be demonstrated, resulting in an object different from that intended. When the blended amount of reinforcing material is 1 part by weight or less, however, the effects thereof as a reinforcing material cannot be demonstrated, and thus the object of obtaining a reinforced polyamide compound is not attained.

There are no particular restrictions on the method employed for mixing the polyamide and the fibrous reinforcing material, and conventional known methods can be employed. Examples of such methods include a method wherein the polyamide and fibrous reinforcing material are uniformly mixed in a high-speed stirrer followed by melting and kneading with an extruding machine having a required kneading capacity, a method wherein the components are kneaded directly in the molding machine at the time of blow molding, followed by such molding without first kneading a uniformly mixed mixture in an extruding machine, and a method wherein the fibrous reinforcing material is side fed into the extruding machine during the course of kneading.

There are no particular restrictions on the elastomer used in the present invention, as long as it is classified as an elastomer, and commercially available elastomers also can be used. Particularly useful examples thereof include ionomer resins and modified polyolefins.

Examples of ionomer resins include ethylene-based ionomer resins wherein a metal ion having a valency of 1-3 is added to a copolymer of an  $\alpha$ -olefin containing ethylene, and an  $\alpha,\beta$ -unsaturated carboxylic acid. Typical examples of such  $\alpha,\beta$ -unsaturated carboxylic acids include acrylic acid, methacrylic acid and itaconic acid, and typical examples of metal ions having a valency of 1-3 include  $\text{Na}^+$ ,  $\text{Ca}^{++}$ ,  $\text{Zn}^{++}$  and  $\text{Al}^{+++}$ . Preferably,  $\text{Na}^+$ ,  $\text{Zn}^{++}$  and  $\text{Al}^{+++}$  are used.

Examples of preferably used modified polyolefins include modified polyolefins obtained by introducing at least one type of modifier selected from maleic acid, fumaric acid, itaconic acid, acrylic acid, crotonic acid and their anhydrides or derivatives, maleimide and epoxy compounds, into a polyolefin obtained by radical polymerization of at least one type of olefin selected from ethylene, propylene, butene-1, butadiene, isoprene, 1,3-pentadiene, pentene-1, 4-methylpentene-1, isobutylene, 1,4-hexadiene, dicyclopentadiene, 2,5-norbornene, 5-ethylenenorbornene, 5-ethyl-2,5-norbornadiene, 5-(1'-propenyl)-2-norbornene, styrene,  $\alpha$ -methylstyrene and vinyltoluene.

Examples of such modified polyolefins include styrene/ethylene-butylene/styrene-g-maleic anhydride block copolymers (written as styrene/butadiene/styrene-g-maleic anhydride block copolymer hydrides) and styrene/isoprene-g-maleic anhydride block copolymers obtained by grafting maleic anhydride following a hydrogenation of ethylene/ethyl acrylate-g-maleic anhydride copolymer, ethylene/ethyl methacrylate-g-maleic anhydride copolymer, ethylene/ethyl acrylate-g-maleimide copolymer, ethylene/ethyl acrylate-g-N-phenylmaleimide copolymer, ethylene/propylene-g-maleic anhydride copolymer, ethylene/butene-1-g-maleic anhydride copolymer, ethylene/propylene/1,4-hexadiene-g-maleic anhydride copolymer, ethylene/propylene/dicyclopentadiene-g-maleic anhydride copolymer, ethylene/propylene/2,5-norbornadiene-g-maleic anhydride copolymer, ethylene/propylene-g-N-phenylmaleimide copolymer, ethylene/butene-1-g-N-phenylmaleimide copolymer, ethylene/glycidylacrylate copolymer, ethylene/glycidylmethacrylate copolymer, styrene/butadiene/styrene-g-maleic anhydride block copolymer and styrene/butadiene/styrene block copolymer (wherein "g" represents a graft). Preferable examples include ethylene/ethylacrylate-g-maleic anhydride copolymer, ethylene/propylene-g-maleic anhydride copolymer, ethylene/propylene/1,4-hexadiene-g-maleic anhydride copolymer, ethylene/propylene-g-N-phenylmaleimide copolymer, styrene/butadiene/styrene-g-maleic anhydride block copolymer, styrene/butadiene/styrene-g-maleic anhydride block copolymer hydride and ethylene/glycidylmethacrylate copolymer.




The amount of modifier added is preferably 0.001-40 mol%, more preferably 0.05-20 mol%, based upon the polyolefin.

One or more types of the above-mentioned elastomer may be mixed and used at any ratio. The amount of elastomer added is 1-150 parts by weight, preferably 5-100 parts by weight, based upon 100 parts by weight of polyamide. When the blended amount of elastomer is less than 1 part by weight, the increase of the depen-

15 dency of the melt viscosity of the mixture on the shear rate is conspicuously reduced and a blow molded product having a superior impact resistance cannot be obtained. When the blended amount of elastomer exceeds 150 parts by weight, however, the heat resistance is lowered and the characteristics of the polyamide cannot be demonstrated, resulting in an object different from the intended object in the form of a polyamide-based plastic blow molded product. The mean particle size of the elastomer dispersed in the polyamide matrix is preferably 20 microns or less, more preferably 0.01-10 microns, to ensure an increased impact resistance.

A flame retarder usable in the present invention is, for example, magnesium hydroxide, brominated polyphenylene ether, brominated polystyrene and a polydibrominated styrene obtained by polymerizing dibrominated styrene. The magnesium hydroxide is preferably in the form of a powder, 95% by weight or more of which is fibrous, having a diameter of 20 microns or less and a particle size of 4 microns or less. Moreover, preferably the surface of the magnesium hydroxide powder is treated with at least one type of silane-based coupling agent such as triethoxy- $\gamma$ -amino-propylsilane, vinyltriethoxysilane; N- $\beta$ -(aminoethyl)- $\gamma$ -amino propyl-trimethoxy-silane and  $\gamma$ -glycidoxypolytrimethoxysilane.

The bromine content and the weight average molecular weight of the flame retarder consisting of polydibrominated styrene (V) obtained by polymerization of dibrominated styrene; brominated polyphenylene ether (III) and brominated polystyrene (IV) as indicated in the following structural formulae, are preferably 50-70% and 5,000-1,000,000, respectively.



wherein, n represents an integer of from 2-400 and m represents an integer of from 20-3500.

45 The above-mentioned flame retarder may be used independently or in the form of a mixture, and the amount added is 5-200 parts by weight, more preferably 7-150 parts by weight, based upon 100 parts by weight of polyamide. When the amount added is less than 5 parts by weight, the flame retarding effects are poor, and when the amount added is more than 200 parts by weight, a lowering of the mechanical properties of the resin compound occurs.

50 A flame retarder assistant usable in the present invention is selected from, for example, antimony trioxide, zinc oxide, ferrous oxide, ferric oxide, stannous oxide, stannic oxide and zinc borate; these may be used independently or in the form of a mixture of two or more types thereof, and the amount added is 1-50 parts by weight, preferably 2-20 parts by weight, based upon 100 parts by weight of polyamide. When the amount added is less than 1 part by weight, the flame retarding properties are poor, and when the amount added exceeds 50 parts by weight, a lowering of the mechanical properties of the polyamide compound occurs.

55 The halogen capturing agent usable in the present invention is particularly effective when using a halogen-based flame retarder. At least one type of compound selected from, for example, calcium carbonate, magnesium oxide, an organophosphate compound and hydrotalcite compounds is used for the halogen capturing agent. The organophosphate compound is a mixed sodium and barium organophosphate, and

$Mg_{0.5}Al_2(OH)_3CO_3 \cdot 5H_2O$ ,  $Mg_{0.2}Al_2(OH)_3CO_3$  and  $Mg_{0.7}Al_{0.3}O_{1.15}$  are preferably used for the hydrotalcite compounds.

Halogen capturing agents prevent corrosion of metal by capturing halogen ions or halogen compounds produced from halogen-based flame retarders and so on. These agents also remarkably reduce the production of gas, foaming and polymer coloring during molding. The added amount of halogen capturing agent is 0-20 parts by weight, preferably 0.01-10 parts by weight, particularly when using halogen-based flame retarders. When a halogen capturing agent is not added when using a halogen-based flame retarder, metal corrosion and a foul odor will occur. Further, when the amount of halogen capturing agent added is more than 20 parts by weight, the mechanical properties of the polyamide compound will be impaired.

It is preferable to add the heat resistant improver usable in the present invention to prevent a deterioration of the molded product during the melting of the polyamide, elastomer and flame retarder, and when in a high temperature environment. At least one type of compound selected from copper acetate, copper iodide, copper chloride, copper bromide, potassium iodide, potassium chloride, sodium hypophosphite, 2,6-di-tert-butyl-4-methyl phenol, n-octadecyl-3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)-p-oxipionate, 2-tert-butyl-6-(3'-tert-butyl-5'-methyl-2'-hydroxybenzyl)-4-methylphenyl acrylate, tetrakis-[methylene-3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)propionate]-methane, 3,9-bis[2-[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy]-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5,5]undecane, N,N'-hexamethylene-bis-(3,5-di-tert-butyl-4-hydroxy-hydrocinamid), 1,3,5-trimethyl-2,4,6-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)benzene, N,N'-bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl]hydrazine, tris-(2,4-di-tert-butylphenyl)phosphite, pentaerythritol-tetrakis-( $\beta$ -lauryl-thiopropionate), 2-(3-tert-butyl-5-methyl-2-hydroxyphenyl)-5-chlorobenzotriazol, 2-[2-hydroxy-3,5-bis( $\alpha,\alpha$ -dimethylbenzyl)phenyl]-2H-benzotriazol, succinic acid-di-methyl-1-(2-hydroxyethyl)-4-hydroxy-2,2,6,6-tetra-methylpiperidine polycondensate (molecular weight: 3,000-4,000), poly[(6-(1,1,3,3-tetra-methylbutyl)imino-1,3,5-triazine-2,4-di-yl)(2,2,6,6-tetra-methyl-4-piperidyl)imino]hexamethylene(2,2,6,6-tetra-methyl-4-piperidyl)imino] (molecular weight: 2,500 - 4,000), N,N'-bis(3-aminopropyl)ethylenediamine/2,4-bis[N-butyl-N-(1,2,2,6,6-penta-methyl-4-piperidyl)amino]-6-chloro-1,3,5-triazine condensate (molecular weight: 2,000-3,000), 2,2-methylene-bis[4-(1,1,3,3-tetra-methylbutyl)-6-(2H-benzotriazol-2-yl)phenol], 2,2-methylene-bis(4,6-di-tert-butylphenyl)octylphosphite, and bis(2,6-di-tert-butyl-4-methylphenyl)penta-erythritol-diphosphite is preferably used for the heat resistant improver.

The added amount of heat resistant improver is preferably 0.001-20 parts by weight, more preferably 0.01-10 parts by weight, based upon 100 parts by weight of polyamide. When the added amount is less than 0.001 parts by weight the desired heat resistance improvement effects, are not demonstrated, and an amount in excess of 20 parts by weight has a detrimental effect on the properties of the raw material and provides no change in the effects thereof as a heat resistant improver.

The polyamide blow molded product of the present invention is preferably a hollow molded product having an inner diameter of 5mm or more, a length of 100mm or more, and/or a non-linear shape, for example, a hollow molded product having a three-dimensionally curved shape.

Also, other components such as pigments, crystal promoters, lubricants, mold releasing agents and so on can be added and introduced into the blow molded product of the present invention, as long as such components do not impair the moldability and physical properties of the blow molded product.

#### EXAMPLES

The present invention will now be further illustrated by the following examples. Note, the properties of the polymer and of the molded products, including the impact resistance of the blow molded products of the preferred embodiments and comparative examples, were evaluated according to the following methods:

(1) Melt viscosity:

Measured using a melt indexer manufactured in compliance with ASTM-D-1238.

(2) Flame resistance:

Measured in accordance with UL-94 standards stipulated by Underwriters Laboratories of the U.S., molding a testpiece 5 inches in length, 1/2 inch wide and 1/16 inch thick.

(3) Elastomer/Dispersed Particle Size:

Observed under an electron microscope after cutting off a portion of the molded product, slicing same into thin sections with a microtome, and staining.

(4) Three-Dimensional Blow Moldability:

Evaluated by molding a parison having an outer diameter of 20 mm and a wall thickness of 4mm, using a blow molding machine equipped with an accumulator and a three-dimensional blow-molding machine, and then evaluating the shape of the molded product of a complex shaped pipe having an outer diameter of 50mm and a length of 800mm.

## (5) Thermal Stability:

The melt residual stability was evaluated according to the appearance of the parison and the production of gas during the three-dimensional blow molding.

(6) Polyamide Melting Point (T<sub>m</sub>) and Crystallization Temperature (T<sub>c</sub>)

The temperature at which the peak value is demonstrated on a melting curve obtained by measuring 8-10mg of sample at a heating rate of 20°C/min using a DSC (Perkin-Elmer Model 7) was taken to be the melting temperature (T<sub>m</sub>). Further, the temperature at which the peak value is demonstrated on a crystallization curve obtained by maintaining 8-10mg of sample at a temperature of (T + 20°C) for 5 minutes, while heating at a heating rate of 20°C/min followed by cooling to a temperature of 30°C at a cooling rate of 20°C/min, was taken to be the crystallization temperature (T<sub>c</sub>).

## (7) Izod Impact Strength:

Measured in compliance with ASTM-D256.

## (8) Heat Deformation Temperature (HDT)

Measured in compliance with ASTM-D648, under a load of 4.6 kgf/cm<sup>2</sup> and a load of 18.6 kgf/cm<sup>2</sup>.

Example 1

Each of the monomers of component 66 (raw material:

hexamethylenediamine/adipic acid), component 6T (raw material: hexamethylenediamine/terephthalic acid) and component 6I (raw material:

hexamethylenediamine/isophthalic acid) were weighed to obtain the composition shown in Table 1, placed in a polymerization oven, and melt polymerized to form a polymer. Following the completion of the polymerization, the polymer was discharged from the bottom of the polymerization oven, pulled into strands, and then formed into pellets by using a pelletizer. The characteristics of these pellets after drying in a vacuum were as follows:

Melting Point (T<sub>m</sub>): 260°C

Crystallization Temperature (T<sub>c</sub>): 226°C

Melt Viscosity  $\mu$ a10: 3200 (poise)

Following a solid phase polymerization of this polyamide with a double-cone vacuum drier, a polyamide was obtained having a melt viscosity at a temperature of 280°C and a shear rate of 10 sec<sup>-1</sup> of  $\mu$ a10 = 62,000 poise. Then, 0.03 parts by weight of CuI and 0.2 parts by weight of KI were respectively added, with respect to 100 parts by weight of polyamide, to the pellets as a heat resistance improver. After blending with a blender, pellets were formed after kneading with a melting extruding machine having a diameter of 30mm. After vacuum drying these pellets, the melt viscosities at shearing rates of 10 sec<sup>-1</sup> and 1000 sec<sup>-1</sup> ( $\mu$ a10 and  $\mu$ a1000, respectively) were measured at a temperature of 280°C, using a melt indexer manufactured in compliance with ASTM-D-1238. This yielded values of  $\mu$ a10 = 63,000 poise and  $\mu$ a1000 = 8,000 poise, both these values satisfying equations (I) and (II).

Next, when the resulting pellets were used to mold a parison having an outer diameter of 20mm and a wall thickness of 2mm at a temperature of 280°C, using a blow molding machine equipped with an extruding machine having a diameter of 40 mm $\phi$ , the parison was observed to be completely free of sagging and blow molding was easily executed, allowing a molded product having a uniform wall thickness to be obtained. When a portion of this molded product was cut off, and the physical properties thereof measured, the results indicated in Table 1 were obtained.

A parison having an outer diameter of 20 mm $\phi$  and a wall thickness of 2mm was then molded, using the same materials and same blow molding machine, into a complex shape pipe having an outer diameter of 50mm and a length of 700mm, using a three-dimensional blow molding machine having a three-dimensional curved shape. This material was able to be molded into a shape matching mold dimensions and having a good appearance, without any solidification of the end of the parison.

Examples 2 - 12

The polyamides having the composite ratios indicated in Table 1 were polymerized by same method as used in Example 1, to obtain polyamides having the characteristics shown in Table 1. A high polymerization was performed by the same method as used in Example 1.

After blending these high polymerization polyamides with the additives indicated in the compound column of Table 1, using a blender, the compounds were extruded by a dual-shaft melting extruding machine having a screw diameter of 30mm $\phi$ , to prepare the compounds having the compound properties shown in Table 1. These compounds were then blow molded, using the same procedure as in Example 1, followed by an evaluation of the characteristics of the molded products. The results are shown in Table 1.



When a fibrous reinforcing material and an elastomer were added the melt viscosity of the compound was increased whereby the conditions for an increase of the degree of polymerization of the polyamide became milder and the dependency of the melt viscosity on the shear rate increased, allowing the preparation of a material able to be advantageously used for blow molding.

#### Comparative Example 1.

Monomers were weighed to provide a composition of 40 wt% of component 66, 24 wt% of component 6T, and 36 wt% of component 6I, and the monomers were then placed in a polymerization oven to obtain a polymer by a melt polymerization. The polyamide of this composition provided a copolyamide with no heat resistance and having a low melting point of 210°C.

#### Comparative Examples 2-9

Polymers formed by a melt polymerization had the compositions indicated in Table 2 for component 66, component 6T, and component 6I. After a high polymerization of the polyamides, using a procedure similar to that of Example 1, and then blending same with the compounds shown in Table 2, a melting and kneading, and an evaluation of the molding, were performed in the same manner as in Example 1, and the results shown in Table 2 were obtained. All of the blow molded products of the polyamides used here demonstrated a rapid solidification of the parison and a poor moldability. Furthermore, in the case of compounds to which a flame retarder agent was added, the flame retarder produced a foul odor.

Table 1

5

10

15

20

25

30

35

40

45

50

55

	Unit	Ex. 1	Ex. 2	Ex. 3
Polyamide	Composition	66/67/61	66/67/61	66/67/61
Polyamide composition ratio	(wt%)	60/30/10	55/30/15	60/30/10
Melting point (Tm)	°C	260	250	260
Crystallization temp. (Tc)	°C	226	200	226
Melt viscosity $\mu\text{a}10$	Poise	62000	58000	9000
$\mu\text{a}10$ of polymer discharged from polymerization vessel following high polymerization		3200	3500	3200
Composition				
Polyamide compounded amount	Wt. part	100	100	100
Type of fibrous reinforcing material*		-	GF	-
Amount			40	
Type of elastomer *2		-	-	SEBS
Amount				20
Type of flame retarder *3		-	-	-
Amount				
Type of flame retarder assistant *4		-	-	-
Amount				
Type of ion capturing agent *5		-	-	-
Amount				
Type of heat resistant improver *6				
Amount		GI/KI 0.03/0.5	Irganox1098 0.3	GI/Irganox1098 0.03/0.2
Melt viscosity $\mu\text{a}10$	Poise	63000	78500	90000
" $\mu\text{a}1000$		8000	8500	9500
$\mu\text{a}10/\mu\text{a}1000$		7.9		9.5
Molded product characteristic				
Blow Moldability		Good	Good	Good
Molded Product Appearance		"	"	"
Foul Odor During Molding		None	None	None
Elastomer Mean Particle Size	$\mu\text{m}$	-	-	0.8
Izod Impact Strength (notched)	kgf cm/cm	5	10	55
HDT (18.6 kgf/cm <sup>2</sup> )	°C	80	220	80
(4.6 kgf/cm <sup>2</sup> )	°C	215	245	200
Flame Resistance	UL-94	HB	HB	HB

Table 1 (Continued)

	Unit	Ex. 4	Ex. 5	Ex. 6
<b>Polyamide</b>	Composition (wtI)		66/6T/6I	66/6T/6I
Polyamide composition ratio		Same as left	55/30/15	60/30/10
Melting point (Tm)	°C		250	260
Crystallization temp. (Tc)			200	226
Melt viscosity $\mu$ al0	Poise	9000	9000	60000
$\mu$ al0 of polymer discharged from polymerization vessel following high polymerization		3200	3500	3200
<b>Composition</b>				
Polyamide compounded amount	Wt. part	100	100	100
Type of fibrous reinforcing material* Amount		-	GF 40	-
Type of elastomer *2 Amount		HM1706 20	GMA-PE 20	-
Type of flame retarder *3 Amount		-	-	P-BrSt 28
Type of flame retarder assistant *4 Amount		-	-	Sb <sub>2</sub> O <sub>3</sub> 6
Type of ion capturing agent *5 Amount		-	-	DHT-4A 0.3
Type of heat resistant improver *6 Amount		CuI/Irganox1098 0.03/0.2	CuI/KI 0.03/0.2	CuI/KI 0.03/0.2
Melt viscosity $\mu$ al0	Poise	85000	110000	62000
$\mu$ al000		9000	9000	8000
$\mu$ al0/ $\mu$ al000		9.4	12.2	7.7
<b>Molded product characteristic</b>				
Blow Moldability		Good	Good	Good
Molded Product Appearance		None	None	None
Foul Odor During Molding		None	None	None
Elastomer Mean Particle Size	$\mu$ m	1.2	1.0	-
Izod Impact Strength (notched)	kgf cm/cm	18	43	5
HDT (18.6 kgf/cm <sup>2</sup> )	°C	80	210	85
(4.6 kgf/cm <sup>2</sup> )	°C	195	240	210
Flame Resistance	UL-94	HB	HB	V-0

Table 1 (Continued)

	Unit	Ex. 7	Ex. 8	Ex. 9
10 Polyanide	Composition	66/6T/6I	66/6T/6I	
Polyamide composition ratio	(wt%)	55/30/10	60/30/10	Same as left
Melting point (Tm)	°C	250	260	*
Crystallization temp. (Tc)	*	200	226	*
Melt viscosity $\mu$ al0	Poise	62000	60000	60000
15 $\mu$ al0 of polymer discharged from polymerization vessel following high polymerization	*	3500	3200	3200
Composition				
Polyamide compounded amount	Wt. part	100	100	100
Type of fibrous reinforcing material*	*	-	GF	-
20 Amount			30	
Type of elastomer *2	*	-	-	H17G6
Amount				20
Type of flame retarder *3	*	Mg(OH) <sub>2</sub>	Br-PPO	Br-PPO
25 Amount		67	30	28
Type of flame retarder assistant *4	*	C.B	Sb <sub>2</sub> O <sub>3</sub>	Sb <sub>2</sub> O <sub>3</sub>
Amount		1.7	7	6
Type of ion capturing agent *5	*	KW-2000	KW-2000	KW-2000
30 Amount		0.5	0.3	0.3
Type of heat resistant improver *6	*	Cul/Irganox1098	Irganox1098	Irganox1098
Amount		0.03/0.2	0.2	0.3
Melt viscosity $\mu$ al0	Poise	65000	75000	92000
* $\mu$ al000	*	9000	8500	9000
35 $\mu$ al0/ $\mu$ al000		7.2	8.8	10.2
<u>Molded product characteristic</u>				
Blow Moldability		Good	Good	Good
Molded Product Appearance		*	*	*
Foul Odor During Molding		None	None	None
Elastomer Mean Particle Size	$\mu$ m	-	-	1.6
40 Izod Impact Strength (notched)	kgf cm/cm	5	10	15
HDT (18.6 kgf/cm <sup>2</sup> )	°C	110	210	85
(4.6 kgf/cm <sup>2</sup> )	°C	225	240	210
Flame Resistance	UL-94	V-0	V-2	V-2

Table 1 (Continued)

	Unit	Ex. 10	Ex. 11	Ex. 12
Polyamide	Composition	66/6T/6I		
Polyamide composition ratio	(wt%)	60/30/10		
Melting point (Tm)	°C	260		
Crystallization temp. (Tc)		226		
Melt viscosity $\mu\text{a}10$	Poise	62000	60000	60000
$\mu\text{a}10$ of polymer discharged from polymerization vessel following high polymerization		3200	3200	3200
Composition				
Polyamide compounded amount	Wt. part	100	100	100
Type of fibrous reinforcing material* Amount			GF 50	GF 50
Type of elastomer *2 Amount		MP-0610 20	HM1706 30	SEBS 30
Type of flame retarder *3 Amount		P-BrSt 35	Br-PSt 32	Br-PPO 30
Type of flame retarder assistant *4 Amount		Sb <sub>2</sub> O <sub>3</sub> 8	Sb <sub>2</sub> O <sub>3</sub> 8	Sb <sub>2</sub> O <sub>3</sub> 6
Type of ion capturing agent *5 Amount		DHT-4A 0.3	DHT-4A 0.5	KW-2000 0.3
Type of heat resistant improver *6 Amount		CuI/Irganox 1098 0.03/0.2	CuI/Irganox 1098 0.03/0.2	CuI/Irganox 1098 0.03/0.2
Melt viscosity $\mu\text{a}10$	Poise	82000	90000	96000
$\mu\text{a}1000$		9000	9500	9300
$\mu\text{a}10/\mu\text{a}1000$		9.1	9.5	10.1
Molded product characteristic				
Blow Moldability				
Molded Product Appearance				
Foul Odor During Molding				
Elastomer Mean Particle Size	$\mu\text{m}$	1.5	1.8	1.7
180° Impact Strength (notched)	kgf cm/cm	15	20	22
HDT (18.6 kgf/cm <sup>2</sup> )	°C	85	215	215
(4.6 kgf/cm <sup>2</sup> )	°C	210	245	245
Flame Resistance	UL-94	V-0	V-2	V-2

Notes of Table 1

- 5 \*1) GF: Glass fiber
- \*2) SEBS: Styrene/butadiene/styrene-g-maleic anhydride block copolymer  
 hydride  
 HMI706: Ionomer (zinc salt of an ethylene/methacrylate copolymer)  
 CMA-PE: Ethylene/glycidylmethacrylate copolymer  
 10 MP0610: Ethylene/propylene-g-maleic anhydride copolymer
- \*3) P-BrSt: Polydibrominated styrene  
 Mg(OH)<sub>2</sub>: Magnesium hydroxide  
 Br-PPO: Brominated polyphenylene ether  
 15 Br-PSt: Brominated polystyrene
- \*4) Sb<sub>2</sub>O<sub>3</sub>: Antimony trioxide  
 CB: Carbon black
- \*5) DHT-4A: Mg<sub>4.5</sub>Al<sub>3</sub>(OH)<sub>13</sub>CO<sub>3</sub>·3.5H<sub>2</sub>O  
 20 KW-2000: Mg<sub>6.7</sub>Al<sub>6.3</sub>O<sub>11.15</sub>
- \*6) CuI/KI: Copper iodide/potassium iodide  
 Irganox 1098: N,N'-hexamethylene(3,5-di-tert-butyl-4-hydroxy-  
 hydrocinnamid)
- 25
- 30
- 35
- 40
- 45
- 50
- 55

Table 2

5

	Unit	Comp. Ex. 1	Comp. Ex. 2	Comp. Ex. 3
Polyamide	Composition	66/6T/6I	66/6T/6I	Same as left
Polyamide composition ratio	(wtI)	40/24/36	50/45/5	*
Melting point (Tm)	°C	210	287	*
Crystallization temp. (Tc)	°C	135	251	*
Melt viscosity $\mu\text{a}10$	Poise	-	3100	
$\mu\text{a}10$ of polymer discharged from polymerization vessel following high polymerization	"	-	61000	
Composition				
Polyamide compounded amount	Wt. part	-	100	100
Type of fibrous reinforcing material*	"	-	-	GF
Amount				40
Type of elastomer *2	"	-	-	
Amount				
Type of flame retarder *3	"	-	-	
Amount				
Type of flame retarder assistant *4	"	-	-	
Amount				
Type of ion capturing agent *5	"	-	-	
Amount				
Type of heat resistant improver *6	"	-	CuI/KI	Irganox1098
Amount			0.03/0.5	0.3
Melt viscosity $\mu\text{a}10$	Poise	-	61000	78000
" $\mu\text{a}1000$	"	-	8000	8500
" $\mu\text{a}10/\mu\text{a}1000$			7.8	
Molded product characteristic				
Blow Moldability		-	Poor	Poor
Molded Product Appearance		-	*	*
Foul Odor During Molding		-	None	None
Elastomer Mean Particle Size	$\mu\text{m}$	-	-	-
Izod Impact Strength (notched)	kgf cm/cm	-	5	-
HDT (18.6 kgf/cm <sup>2</sup> )	°C	-	-	-
(4.6 kgf/cm <sup>2</sup> )	°C	-	-	-
Flame Resistance	FM-DA	-	-	-

45

50

55

Table 2 (Continued)

	Unit	Comp. Ex. 4	Comp. Ex. 5	Comp. Ex. 6
<b>Polyamide</b>	Composition	66/6T/6I	Same as left	66/6T/6I
Polyamide composition ratio	(wt%)	50/45/5		45/45/10
Melting point (Tm)	°C	287	*	280
Crystallization temp. (Tc)	"	251	*	235
Melt viscosity $\mu\text{a}10$	Poise	3100	*	3000
$\mu\text{a}10$ of polymer discharged from polymerization vessel following high polymerization	"	9000	*	60000
<b>Composition</b>				
Polyamide compounded amount	Wt. part	100	100	100
Type of fibrous reinforcing material *	"		GF	
Amount			40	
Type of elastomer *2	"	SEBS	GMA-PE	
Amount		20	20	
Type of flame retardant *3	"			Br-PFO
Amount				30
Type of flame retarder assistant *4	"			Sb <sub>2</sub> O <sub>3</sub>
Amount				7
Type of ion capturing agent *5	"			
Amount				
Type of heat resistant improver *6	"	CuI/Irganox1098	CuI/KI	
Amount		0.03/0.2	0.03/0.2	
Melt viscosity $\mu\text{a}10$	Poise	85000	105000	61000
$\mu\text{a}1000$	"	9000	9000	8000
$\mu\text{a}10/\mu\text{a}1000$				7.6
<b>Molded product characteristic</b>				
Blow Moldability		Poor	Poor	Poor
Molded Product Appearance		*	*	*
Foul Odor During Molding		None	None	Present
Elastomer Mean Particle Size	$\mu\text{m}$	1.0	1.5	-
Izod Impact Strength (notched)	kgf cm/cm			
HDT (18.6 kgf/cm <sup>2</sup> )	°C			
(4.6 kgf/cm <sup>2</sup> )	°C	-	-	-
Flame Resistance	UL-94	-	-	V-1



Table 2 (Continued)

	Unit	Comp. Ex. 7	Comp. Ex. 8	Comp. Ex. 9
<b>Polyamide</b>	Composition	66/67/61		
Polyamide composition ratio	(wt%)	45/45/10	Same as left	Same as left
Melting point (Tm)	°C	280		
Crystallization temp. (Tc)	°C	235	*	*
Melt viscosity $\mu\text{a}10$	Poise	3000	*	3000
$\mu\text{a}10$ of polymer discharged from polymerization vessel following high polymerization		6000		9000
<b>Composition</b>				
Polyamide compounded amount	Wt. part	100	100	100
Type of fibrous reinforcing material*			GF	GF
Amount			30	50
Type of elastomer *2		HM1706		HM1706
Amount		20	-	30
Type of flame retarder *3		Br-PSt	Br-PFO	Br-PSt
Amount		28	30	32
Type of flame retarder assistant *4		Sb <sub>2</sub> O <sub>3</sub>	Sb <sub>2</sub> O <sub>3</sub>	Sb <sub>2</sub> O <sub>3</sub>
Amount		7	7	8
Type of ion capturing agent *5				
Amount		-	-	-
Type of heat resistant improver *6				
Amount		-	-	-
Melt viscosity $\mu\text{a}10$	Poise	82000	71100	90000
* $\mu\text{a}1000$		9000	8800	9500
$\mu\text{a}10/\mu\text{a}1000$		9.1	8.1	9.5
Molded product characteristic				
Blow Moldability		Poor	Poor	Poor
Molded Product Appearance		*	*	*
Foul Odor During Molding		Present	Present	Present
Elastomer Mean Particle Size	$\mu\text{m}$	2.0	-	1.8
Izod Impact Strength (notched)	kgf cm/cm			
BDT (18.6 kgf/cm <sup>2</sup> )	°C			
(4.6 kgf/cm <sup>2</sup> )	°C			
Flame Resistance	UL-94	V-2	V-1	V-2

## Claims

1. A polyamide blow molded product comprising: a crystalline polyamide comprising (a) 50 - 90% by weight of a hexamethylene adipamide component, (b) 5 - 40% by weight of a hexamethylene terephthalamide component, and (c) 5 - 30% by weight of a hexamethylene isophthalamide component, wherein the melting point (Tm) and crystallization temperature (Tc) of the crystalline polyamide are Tm  $\geq$  225°C and Tc  $\geq$  230°C, respectively.
2. A polyamide blow molded product comprising: a crystalline polyamide comprising (a) 53 - 85% by weight of a hexamethylene adipamide component, (b) 15 - 40% by weight of a hexamethylene terephthalamide component, and (c) 5 - 20% by weight of a hexamethylene isophthalamide component, wherein the melting

point (Tm) and crystallization temperature (Tc) of the crystalline polyamide are  $T_m \approx 240^\circ\text{C}$  and  $T_c \approx 230^\circ\text{C}$ , respectively.

3. A polyamide blow molded product as claimed in claim 1, wherein, when measured at a constant temperature of  $20^\circ\text{C}$  higher than the melting point (Tm) of the polyamide ( $T_m + 20^\circ\text{C}$ ), the melt viscosity of said polyamide is such that:

$$2,000,000 \geq \ln \mu_{a10} \geq 2,000 \quad (I)$$

$$\mu_{a10}/\mu_{a1000} \geq 3.3 \quad (II)$$

wherein:

Tm: melting point of polyamide ( $^\circ\text{C}$ )

$\mu_{a10}$ : melt viscosity at a temperature of  $T_m + 20^\circ\text{C}$  and a shear rate of 10 (1/sec)(poise)

$\mu_{a1000}$ : melt viscosity at a temperature of  $T_m + 20^\circ\text{C}$  and a shear rate of 1000 (1/sec)(poise)

4. A polyamide blow molded product wherein, when measured at a constant temperature of  $20^\circ\text{C}$  higher than the melting point (Tm) of the polyamide ( $T_m + 20^\circ\text{C}$ ), the melt viscosity of said polyamide is such that:

$$1,500,000 \geq \ln \mu_{a10} \geq 3,000 \quad (I)$$

and

$$\mu_{a10}/\mu_{a1000} \geq 4.0 \quad (II)$$

wherein:

Tm: melting point of polyamide ( $^\circ\text{C}$ )

$\mu_{a10}$ : melt viscosity at a temperature of  $T_m + 20^\circ\text{C}$  and a shear rate of 10 (1/sec)(poise)

$\mu_{a1000}$ : melt viscosity at a temperature of  $T_m + 20^\circ\text{C}$  and a shear rate of 1000 (1/sec)(poise)

5. A polyamide blow molded product as claimed in any preceding claim, further comprising 1-200 parts by weight of a fibrous reinforcing material, based upon 100 parts by weight of the polyamide.

6. A polyamide blow molded product as claimed in claim 5, wherein the amount of fibrous reinforcing material is 10-100 parts by weight.

7. A polyamide blow molded product as claimed in claim 5 or 6, wherein the fibrous reinforcing material is at least one material selected from aramid fiber, glass fiber, carbon fiber, alumina fiber, silicon carbide fiber, boron fiber, zirconia fiber and potassium titanate whisker.

8. A polyamide blow molded product as claimed in claim 7, wherein the fibrous reinforcing material is glass fiber, carbon fiber or a mixture thereof.

9. A polyamide blow molded product as claimed in any one of claims 5 to 8, wherein the fibrous reinforcing material is surface treated with a silane-based coupling agent.

10. A polyamide blow molded product as claimed in claim 9, wherein the silane-based coupling agent is at least one compound selected from triethoxy- $\gamma$ -aminopropylsilane, vinyltriethoxysilane, N- $\beta$ -(aminoethyl)- $\gamma$ -aminopropyltrimethoxysilane and  $\gamma$ -glycidoxypropyltrimethoxysilane.

11. A polyamide blow molded product as claimed in any preceding claim, further comprising 1-150 parts by weight of an elastomer, based upon 100 parts by weight of the polyamide.

12. A polyamide blow molded product as claimed in claim 11, wherein the amount of elastomer is 5-100 parts by weight.

13. A polyamide blow molded product as claimed in claim 11 or 12, wherein the elastomer is an ethylene-based ionomer resin.

14. A polyamide blow molded product as claimed in claim 13, wherein the ethylene-based ionomer is an ionic polymer in which a metal ion having a valency of 1-3 is added to a copolymer of ethylene and one unsaturated carboxylic acid selected from acrylic acid, methacrylic acid and itaconic acid.

15. A polyamide blow molded product as claimed in claim 14, wherein the metal ion is one metal ion selected from  $\text{Na}^+$ ,  $\text{Zn}^{2+}$  and  $\text{Al}^{3+}$ .

16. A polyamide blow molded product as claimed in claim 11 or 12, wherein the elastomer is a modified polyole-

fin obtained by introduction of at least one modifier selected from maleic acid, fumaric acid, itaconic acid, acrylic acid, crotonic acid, their anhydrides and derivatives, maleimide and epoxy compounds into a polyolefin obtained by radical polymerization of at least one olefin selected from ethylene, propylene, butene-1, butadiene, isoprene, 1,3-pentadiene, pentene-1, 4-methylpentene-1, isobutylene, 1,4-hexadiene, dicyclopentadiene, 2,5-norbornene, 5-ethylenenorbornene, 5-ethyl-2,5-norbornadiene, 5-(1'-propenyl)-2-norbornene, styrene,  $\alpha$ -methylstyrene and vinyltoluene.

17. A polyamide blow molded product as claimed in claim 16, wherein the amount of modifier added is 0.001-40 mol% with respect to the polyolefin.
18. A polyamide blow molded product as claimed in claim 16, wherein the amount of modifier added is 0.05-20 mol% with respect to the polyolefin.
19. A polyamide blow molded product as claimed in claim 16, 17 or 18, wherein the modified polyolefin is at least one polymer selected from styrene/ethylene-butylene/styrene-g-maleic anhydride block copolymer (written as hydrogenated styrene/butadiene/styrene-g-maleic anhydride block copolymer) and styrene/isoprene-g-maleic anhydride block copolymer obtained by grafting maleic anhydride after the hydrogenation of ethylene/ethyl acrylate-g-maleic anhydride copolymer, ethylene/ethyl methacrylate-g-maleic anhydride copolymer, ethylene/ethyl acrylate-g-maleimide copolymer, ethylene/ethyl acrylate-g-N-phenylmaleimide copolymer, ethylene/propylene-g-maleic anhydride copolymer, ethylene/butene-1-g-maleic anhydride copolymer, ethylene/propylene/1,4-hexadiene-g-maleic anhydride copolymer, ethylene/propylene/dicyclopentadiene-g-maleic anhydride copolymer, ethylene/propylene/2,5-norbornadiene-g-maleic anhydride copolymer, ethylene/propylene-g-N-phenylmaleimide copolymer, ethylene/butene-1-g-N-phenylmaleimide copolymer, ethylene/glycidylacrylate copolymer, ethylene/glycidylmethacrylate copolymer, styrene/butadiene/styrene-g-maleic anhydride block copolymer and styrene/butadiene/styrene block copolymer, wherein "g" represents graft.
20. A polyamide blow molded product as claimed in claim 16, wherein the modified polyolefin is at least one polymer selected from ethylene/ethyl acrylate-g-maleic anhydride copolymer, ethylene/propylene-g-maleic anhydride copolymer, ethylene/propylene/1,4-hexadiene-g-maleic anhydride copolymer, ethylene/propylene-g-N-phenylmaleimide copolymer, styrene/butadiene/styrene-g-maleic anhydride block copolymer, styrene/butadiene/styrene-g-maleic anhydride block copolymer hydride and ethylene/glycidylmethacrylate copolymer, wherein "g" represent graft.
21. A polyamide blow molded product as claimed in any preceding claim, further comprising 5-200 parts by weight of a flame retarder, 1-50 parts by weight of a flame retarder assistant and 0-20 parts by weight of a halogen capturing agent, based upon 100 parts by weight of the polyamide.
22. A polyamide blow molded product as claimed in claim 21, wherein the amounts of the flame retarder, flame retarder assistant and halogen capturing agent are 7-150 parts by weight, 2-20 parts by weight, and 0.01-10 parts by weight, respectively.
23. A polyamide blow molded product as claimed in claim 21 or 22, wherein the flame retarder is at least one compound selected from hydroxide, brominated polyphenylene ether, brominated polystyrene and poly(dibrominated styrene) derived from dibrominated styrene.
24. A polyamide blow molded product as claimed in claim 23, wherein the magnesium hydroxide is in the form of a fiber having a diameter of 20 microns or less or a powder of which 95% by weight or more is a particle size of 4 microns or less.
25. A polyamide blow molded product as claimed in claim 23 or 24, wherein the surface of the magnesium hydroxide is treated with a silane-based coupling agent.
26. A polyamide blow molded product as claimed in claim 25, wherein the silane-based coupling agent is at least one compound selected from triethoxy- $\gamma$ -aminopropylsilane, vinyltriethoxysilane, N- $\beta$ -(aminoethyl)- $\gamma$ -aminopropyltrimethoxy-silane and  $\gamma$ -glycidyloxypropyltrimethoxysilane.
27. A polyamide blow molded product as claimed in claim 23, wherein the bromine content and the weight average molecular weight of the flame retarder consisting of poly(dibrominated styrene) obtained by

polymerization of dibrominated styrene, brominated polyphenylene ether and brominated polystyrene are 50-70% and 5,000-1,000,000, respectively.

28. A polyamide blow molded product as claimed in any one of claim 21 to 27, wherein the flame retarder assistant is at least one compound selected from antimony trioxide, zinc oxide, ferrous oxide, ferric oxide, stannous oxide, stannic oxide and zinc borate.

29. A polyamide blow molded product as claimed in any one of claims 21 to 27, wherein the halogen capturing agent is at least one compound selected from calcium carbonate, magnesium oxide, organophosphate compounds and hydrotalcite compounds.

30. A polyamide blow molded product as claimed in claim 29, wherein the organophosphate compound is a mixed sodium and barium organophosphate, and the hydrotalcite compounds are  $Mg_{4.5}Al_2(OH)_{13}CO_3 \cdot 3H_2O$ ,  $Mg_{4.2}Al_2(OH)_{12.4}CO_3$  and  $Mg_{0.7}Al_{0.3}O_{1.16}$ .

31. A polyamide blow molded product as claimed in any one of claims 5 to 30, wherein, when measured at a constant temperature of 20°C higher than the melting point (Tm) of the polyamide (Tm + 20°C), the melt viscosity of said polyamide compound is such that:

$$2,000,000 \geq \ln \mu a10 \geq 2,000 \quad (I)$$

$$\mu a10/\mu a1000 \geq 3.3 \quad (II)$$

wherein:

Tm: melting point of polyamide (°C)

$\mu a10$ : melt viscosity at a temperature of Tm + 20°C and a shear rate of 10 (1/sec)(poise)

$\mu a1000$ : melt viscosity at a temperature of Tm + 20°C and a shear rate of 1000 (1/sec)(poise).

32. A polyamide blow molded product as claimed in claim 31, wherein, when measured at a constant temperature of 20°C higher than the melting point (Tm) of the polyamide (Tm + 20°C), the melt viscosity of said polyamide compound is such that:

$$1,500,000 \geq \ln \mu a10 \geq 3,000 \quad (I)$$

$$\mu a10/\mu a1000 \geq 4.0 \quad (II)$$

wherein:

Tm: melting point of polyamide (°C)

$\mu a10$ : melt viscosity at a temperature of Tm + 20°C and a shear rate of 10 (1/sec)(poise)

$\mu a1000$ : melt viscosity at a temperature of Tm + 20°C and a shear rate of 1000 (1/sec)(poise).

33. A polyamide blow molded product as claimed in any one of claim 11 to 32, wherein the mean particle size of the elastomer dispersed in the polyamide matrix is 20 microns or less.

34. A polyamide blow molded product as claimed in claim 33, wherein the mean particle size of the elastomer dispersed in the polyamide matrix is 0.10-10 microns.

35. A polyamide blow molded product as claimed in any preceding claim, further comprising 0.001-20 parts by weight of a heat resistant improver, based upon 100 parts by weight of the polyamide.

36. A polyamide blow molded product as claimed in claim 35, wherein the heat resistant improver is 0.01-10 parts by weight, based upon 100 parts by weight of polyamide.

37. A polyamide blow molded product as claimed in claim 35 or 36, wherein the heat resistance improver is at least one compound selected from copper acetate, copper iodide, copper chloride, copper bromide, potassium iodide, potassium chloride, sodium hypophosphite, 2,6-di-tert-butyl-4-methyl phenol, n-octadecyl-3-(3',5'-di-tert-butyl-4'-hydroxyphenyl)-propionate, 2-tert-butyl-6-(3'-tert-butyl-5'-methyl-2'-hydroxybenzyl)-4-methylphenyl acrylate, tetrakis-[methylene-3-(3',5'-di-tert-butyl-4'-hydroxy-phenyl)propionate]-methane, 3,9-bis[2-[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy]-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5,5]undecane, N,N'-hexamethylene-bis-(3,5-di-tert-butyl-4-hydroxy-hydrocinnamid), 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene, N,N'-bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl]hydrazine, tris-(2,4-di-tert-butylphenyl)phosphite, pentaerythritol-tetrakis-(p-lauryl-thiopropionate), 2-(3-tert-butyl-5-methyl-2-hydroxyphenyl)-5-chlorobenzotriazol, 2-[2-hydroxy-3,5-bis(α,α-dimethylbenzyl)phenyl]-2H-benzotriazol, succinic acid-di-methyl-(2-hydroxyethyl)-4-hydroxy-2,2,6,6-tetra-methyl-piperidine polycondensate having a (molecular weight of 3,000-4,000, poly[6-(1,1,3,3-tetra-methyl-

butyl)imino-1,3,5-triazine-2,4-di-yl)(2,2,6,6-tetra-methyl-4-piperizil)imino)hexamethylene(2,2,6,6-tetra-methyl-4-piperizil)imino)) having a molecular weight of 2,500-4,000, N,N'-bis(3-aminopropyl)ethylenediamine/2,4-bis[N-butyl-N-(1,2,2,6,6-penta-methyl-4-piperizil)amino]-6-chloro-1,3,5-triazine condensate having a molecular weight of 2,000-3,000, 2,2-methylene-bis[4-(1,1,3,3-tetra-methylbutyl)-6-(2H-benzotriazol-2-yl)phenol], 2,2-methylene-bis[4,6-di-tert-butylphenyl]octylphosphite, and bis(2,6-di-tert-butyl-4-methylphenyl)penta-erythritol-di-phosphite.

38. A polyamide blow molded product as claimed in any preceding claim, which is a hollow molded product having an inner diameter of 5 mm or more, a length of 100 mm or more, and a non-linear shape.
39. A polyamide blow molded product as claimed in claim 38, wherein the inner diameter and length of the polyamide blow molded product are 10 mm or more and 300 mm or more, respectively.
40. A polyamide blow molded product as claimed in claim 38, wherein the hollow molded product has a three-dimensionally curved shape.

European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number

EP 92 30 2327

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 5)
X	EP-A-0 394 029 (AMOCO) * Claims; page 5, line 10 - page 9, line 40; page 9, line 56 - page 10, line 17 *	1-10	C 08 G 69/26 C 08 L 77/02 C 08 L 23/08
Y	---	11-40	C 08 K 7/02 C 08 K 9/06
Y	PATENT ABSTRACTS OF JAPAN, vol. 12, no. 132 (C-490), 22nd April 1988, & JP-A-62 252 453 (UBE IND. LTD) 04-11-1987 ---	1,11-40	C 08 L 51/06 // (C 08 K 7/02 C 08 L 77:02 C 08 L 23:08 )
Y	PATENT ABSTRACTS OF JAPAN, vol. 12, no. 132 (C-490), 22nd April 1988, & JP-A-62 253 653 (ASAHI) 05-11-1987 ---	1,11-40	(C 08 K 7/02 C 08 L 77:02 C 08 L 51:06 )
Y	EP-A-0 176 978 (BASF) * Claims; page 1, line 25 - page 3, line 25 *	1,11-40	
Y	---		
Y	GB-A-1 284 489 (ICI) * Claims; column 1, line 9 - column 7, line 39 *	1,11-40	
Y	---		
Y	EP-A-0 276 828 (DU PONT DE NEMOURS) * Whole document *	1,11-40	
Y	---		
Y	EP-A-0 403 109 (MITSUBISHI) * Claims; page 2, line 45 - page 4, line 53 *	1,11-40	
Y	---		
The present search report has been drawn up for all claims			
Phase of search		Date of completion of the search	Examiner
THE HAGUE		17-06-1992	LEROY ALAIN
CATEGORY OF CITED DOCUMENTS			
<p>X: particularly relevant if taken alone  Y: particularly relevant if combined with another document of the same category  A: technological background  O: non-written disclosure  P: intermediate document</p> <p>T: theory or principle underlying the invention  E: earlier patent document, but published on, or after the filing date  D: document cited in the application  I: document cited for other reasons  a: member of the same patent family, corresponding document</p>			

EPO FORM 1501 (03.81) (P0001)